

Viking PRO HZ test results**NOT HZ CERTIFIED - LIQUID B FAILURE**

CHEMICAL	PERMEATION BT* TIME (MINUTES)			EN 14225-2 PROTECTION INDEX
	MATERIAL	SEAM	ZIPPER	
Sulphuric acid , H2 SO4 (aqueous)	> 480	> 480	> 480	High
Sodium Hydroxide , NaOH,50% (aqueous)	> 480	> 480	> 480	High
Isoproponoal	> 480	> 480	> 480	High
Toluene 0.05% (aqueous)	> 480	> 480	> 480	High
Liquid B	20	19	48	Liquid B failure
Liquid F	213	117	> 480	High

CLASSIFICATION OF RESULTS:**Minimum breakthrough time required : 20 minutes****Low protection index : 20 - 60 minutes****High protection index : > 60 minutes**